

## TECHNICAL DATA SHEET

### Iron Oxide Black TG330

<b>Edition of</b>	2012-12-11
<b>Type</b>	Granular Black Pigment
<b>Molecular formula</b>	Fe <sub>3</sub> O <sub>4</sub>
<b>Molecular weight</b>	231.54
<b>Delivery Form</b>	Granular
<b>Chemical Class</b>	Synthetic Iron Oxide
<b>Color Index</b>	Pigment Black 11 (77499)
<b>CAS No.</b>	1317-61-9
<b>Use ReCommedation</b>	Building

#### COLOR VALUES AND TINTING STRENGTH

Reference	Standard: DIN 6174		
	<u>Min</u>	<u>Max</u>	<u>Test Method</u>
Reduction with titanium dioxide (1:2)		R-706	No.038.2009-08-01
ΔL*	-0.7	0.7	
Δa*	-0.7	0.7	
Δb*	-0.7	0.7	
ΔE*ab		1.0	
Binder		R-05	
Relative tinting strength [%]	95	105	No.038.2009-08-01

#### TECHNICAL DATA

	<u>Min</u>	<u>Max</u>	<u>Test Method</u>
Fe <sub>3</sub> O <sub>4</sub>	87.0		DIN 55913-2
SiO <sub>2</sub> +Al <sub>2</sub> O <sub>3</sub> Content [%]		0.6	DIN 55913
Water soluble substances [%]		4.0	DIN ISO 787-3
Moisture at 105°C [%]		1.0	DIN ISO 787-2
Oil absorption approx [%]		25	DIN ISO 787-5
Sieve residue on 0.045mm mesh [%]		0.1	DIN 53195
Tinting strengths vs. standard range	95	105	DIN 6174
ΔE		1.0	DIN 6174
PH Value	4.0	8.0	DIN ISO 787-9
Density		4.5	DIN ISO 787-10
Tamped Density		1.0	DIN ISO 787-11
Granular size: 0.3 mm – 0.6 mm/ 0.6 mm – 1.0 mm	80.0		

#### STANDARD PACKAGING 25kg/bag

Address: Rm 1702, West Wing, Donghaishijia, No.41, Donghaixi Road, Qingdao 266071, China  
 Tel: 86-532-85979677/8 Fax: 86-532-85979676  
 Website: [www.qdter.com](http://www.qdter.com) E-mail: [webs@qdter.com](mailto:webs@qdter.com)

TER QINGDAO INDUSTRY



Address: Rm 1702, West Wing, Donghaishijia, No.41, Donghaixi Road, Qingdao 266071, China  
Tel: 86-532-85979677/8 Fax: 86-532-85979676  
Website: [www.gdter.com](http://www.gdter.com) E-mail: [webs@gdter.com](mailto:webs@gdter.com)